

**PCT**

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C23C 16/30, 16/40, 30/00, B23B 27/14</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 97/20082</b> <b>(43) International Publication Date:</b> 5 June 1997 (05.06.97)
<b>(21) International Application Number:</b> PCT/SE96/01578 <b>(22) International Filing Date:</b> 29 November 1996 (29.11.96)  <b>(30) Priority Data:</b> 9504304-8 30 November 1995 (30.11.95) SE 9602413-8 17 June 1996 (17.06.96) SE  <b>(71) Applicant (for all designated States except US):</b> SANDVIK AB, (publ) [SE/SE]; S-811 81 Sandviken (SE).  <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> LINDSKOG, Per [SE/SE]; Staffan Stallares Väg 17, S-125 35 Älvsjö (SE). GUSTAFSON, Per [SE/SE]; Segerminnesvägen 37, S-141 40 Huddinge (SE). LJUNGBERG, Björn [SE/SE]; Kulstötärvägen 96, S-122 44 Enskede (SE). ÖSTLUND, Åke [SE/SE]; Sedelvägen 12, S-129 32 Hägersten (SE).  <b>(74) Agents:</b> ÖSTLUND, Alf et al.; Sandvik AB (publ), Patent Dept., S-811 81 Sandviken (SE).		<b>(81) Designated States:</b> BR, CN, IL, JP, KR, US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> COATED TURNING INSERT AND METHOD OF MAKING IT.  <b>(57) Abstract</b>  The present invention discloses a coated turning insert particularly useful for turning in stainless steel. The insert is characterised by a WC-Co-based cemented carbide substrate having a highly W-alloyed Co-binder phase and a coating including an inner layer of $TiC_xN_yO_z$ with columnar grains followed by a layer of fine grained $\kappa-Al_2O_3$ and a top layer of TiN. The layers are deposited by using CVD-methods.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgystan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

## COATED TURNING INSERT AND METHOD OF MAKING IT

The present invention relates to a coated cutting tool (cemented carbide insert) particularly useful for wet turning of toughness demanding stainless steels components like square bars, flanges and tubes, with raw surfaces such as cast skin, forged skin, hot or cold rolled skin or pre-machined surfaces.

When turning stainless steels with cemented carbide tools the cutting edge is worn according to different wear mechanisms, such as adhesive wear, chemical wear, abrasive wear and by edge chipping caused by cracks formed along the cutting edge, the so called comb cracks.

Different cutting conditions require different properties of the cutting insert. For example, when cutting in steels with raw surface zones a coated cemented carbide insert must consist of a tough carbide and have very good coating adhesion. When turning in stainless steels the adhesive wear is generally the dominating wear type.

Measures can be taken to improve the cutting performance with respect to a specific wear type. However, very often such action will have a negative effect on other wear properties.

So far it has been very difficult to improve all tool properties simultaneously. Commercial cemented carbide grades have therefore been optimised with respect to one or few of the wear types and hence to specific application areas.

Swedish patent application 9503056-5 discloses a coated cutting insert particularly useful for turning in hot and cold forged low alloyed steel components. The inserts is characterised by a cemented carbide substrate consisting of Co-WC and cubic carbides having a 15-35  $\mu\text{m}$

thick surface zone depleted from cubic carbides, a coating including a layer of  $\text{TiC}_x\text{N}_y\text{O}_z$  with columnar grains, a layer of smooth, fine grained  $\kappa\text{-Al}_2\text{O}_3$ , and preferably an outer layer of TiN.

5 Swedish patent application 9504304-8 discloses a coated cutting insert particularly useful for wet and dry milling of low and medium alloyed steels. The insert is characterised by a cemented carbide substrate consisting of Co-WC and cubic carbides, a coating including a  
10 layer of  $\text{TiC}_x\text{N}_y\text{O}_z$  with columnar grains, a layer of smooth, fine grained  $\kappa\text{-Al}_2\text{O}_3$  and preferably an outer layer of TiN.

It has now been found that combinations of the substrates and coatings described in the above patent applications give rise to excellent cutting performance in  
15 stainless steels turning. A cemented carbide substrate with a cubic carbide depleted surface zone combined with a coating in accordance with patent application, 9503056-5, has been found to be especially suitable for  
20 high speed turning in easy stainless steel, such as turning of machineability improved 304L. In more difficult work piece materials such as 316-Ti and in operations with a high degree of thermal cycling such as turning of square bars a straight WC-Co substrate of the  
25 type described in patent application 9504304-8 has been found the most suitable.

A turning tool insert according to the invention useful for turning of steel consists of a cemented carbide substrate with a highly W-alloyed binder phase and  
30 with a well balanced chemical composition and grain size of the WC, a columnar  $\text{TiC}_x\text{N}_y\text{O}_z$ -layer, a  $\kappa\text{-Al}_2\text{O}_3$ -layer, a TiN-layer and optionally followed by smoothening the cutting edges by brushing the edges with e.g. a SiC based brush.

The cobalt binder phase is highly alloyed with W. The content of W in the binder phase can be expressed as the CW-ratio =  $M_s / (\text{wt\% Co} \cdot 0.0161)$ , where  $M_s$  is the measured saturation magnetisation of the cemented carbide substrate in kA/m and wt% Co is the weight percentage of Co in the cemented carbide. The CW-value is a function of the W content in the Co binder phase. A low CW-value corresponds to a high W-content in the binder phase. According to the present invention improved cutting performance is achieved if the cemented carbide substrate has a CW-ratio of 0.78-0.93.

According to the present invention a turning tool insert is provided particularly useful for difficult stainless steel turning is provided with a cemented carbide substrate with a composition of 6-15 wt% Co, preferably 9-12 wt% Co, most preferably 10-11 wt% Co, 0.2-1.8 wt% cubic carbides, preferably 0.4-1.8 wt% cubic carbides, most preferably 0.5-1.7 wt% cubic carbides of the metals Ta, Nb and Ti and balance WC. The cemented carbide may also contain other carbides from elements from group IVb, Vb or VIb of the periodic table. The content of Ti is preferably on a level corresponding to a technical impurity. The preferred average grain size of the WC depend on the binder phase content. At the preferred composition of 10-11 wt-% Co, the preferred grain size is 1.5-2  $\mu\text{m}$ , most preferably about 1.7  $\mu\text{m}$ . The CW-ratio shall be 0.78-0.93, preferably 0.80-0.91, and most preferably 0.82-0.90. The cemented carbide may contain small amounts, <1 volume %, of  $\eta$ -phase ( $M_6C$ ), without any detrimental effect. From the CW-value it follows that no free graphite is allowed in the cemented carbide substrate according to the present embodiment.

The coating comprises

- a first (innermost) layer of  $\text{TiC}_x\text{N}_y\text{O}_z$  with  $x+y+z=1$ , preferably  $z<0.5$ , with equiaxed grains with

size  $<0.5 \mu\text{m}$  and a total thickness  $<1.5 \mu\text{m}$  and preferably  $>0.1 \mu\text{m}$ .

- a layer of  $\text{TiC}_x\text{N}_y\text{O}_z$  with  $x+y+z=1$ , preferably with  $z=0$  and  $x>0.3$  and  $y>0.3$ , with a thickness of  $1-15 \mu\text{m}$ , preferably  $2-8 \mu\text{m}$ , with columnar grains and with an average diameter of  $<5 \mu\text{m}$ , preferably  $0.1-2 \mu\text{m}$ . Most preferred thickness of the  $\text{TiC}_x\text{N}_y\text{O}_z$  layer is  $2-5 \mu\text{m}$ , particularly in extremely edgeline-toughness demanding work-piece materials such as Ti-stabilised stainless steel.

- a layer of a smooth, fine-grained (grain size about  $0.5-2 \mu\text{m}$ )  $\text{Al}_2\text{O}_3$  consisting essentially of the  $\kappa$ -phase. However, the layer may contain small amounts,  $1-3 \text{ vol-\%}$ , of the  $\theta$ - or the  $\alpha$ -phases as determined by XRD-measurement. The  $\text{Al}_2\text{O}_3$ -layer has a thickness of  $0.5-6 \mu\text{m}$ , preferably  $0.5-3 \mu\text{m}$ , and most preferably  $0.5-2 \mu\text{m}$ . Preferably, this  $\text{Al}_2\text{O}_3$ -layer is followed by a further layer ( $<1 \mu\text{m}$ , preferably  $0.1-0.5 \mu\text{m}$  thick) of  $\text{TiN}$ , but the  $\text{Al}_2\text{O}_3$  layer can be the outermost layer. This outermost layer,  $\text{Al}_2\text{O}_3$  or  $\text{TiN}$ , has a surface roughness  $R_{\text{max}}<0.4 \mu\text{m}$  over a length of  $10 \mu\text{m}$ . The  $\text{TiN}$ -layer, if present, is preferably removed along the cutting edge.

According to the method of the invention a WC-Co-based cemented carbide substrate is made with a highly W-alloyed binder phase with a CW-ratio of  $0.78-0.93$ , preferably  $0.80-0.91$ , and most preferably  $0.82-0.90$ , a content of cubic carbides of  $0.2-1.8 \text{ wt\%}$ , preferably  $0.4-1.8 \text{ wt\%}$ , most preferably  $0.5-1.7 \text{ wt\%}$  of the metals Ta, Nb and Ti, with  $6-15 \text{ wt\% Co}$ , preferably  $9-12 \text{ wt\% Co}$ , most preferably  $10-11 \text{ wt\% Co}$  at which Co-content the WC grain size  $1.5-2 \mu\text{m}$ , most preferably about  $1.7 \mu\text{m}$ . The body is coated with:

- a first (innermost) layer of  $\text{TiC}_x\text{N}_y\text{O}_z$  with  $x+y+z=1$ , preferably  $z<0.5$ , with a thickness of  $<1.5 \mu\text{m}$ ,

and with equiaxed grains with size  $<0.5 \mu\text{m}$  using known CVD-methods.

- a layer of  $\text{TiC}_x\text{N}_y\text{O}_z$   $x+y+z=1$ , preferably with  $z=0$  and  $x > 0.3$  and  $y > 0.3$ , with a thickness of  $1-13 \mu\text{m}$ , preferably  $2-8 \mu\text{m}$ , with columnar grains and with an average diameter of  $<5 \mu\text{m}$ , preferably  $<2 \mu\text{m}$ , using preferably MTCVD-technique (using acetonitrile as the carbon and nitrogen source for forming the layer in the temperature range of  $700-900^\circ\text{C}$ ). The exact conditions, however, depend to a certain extent on the design of the equipment used.

- a smooth  $\text{Al}_2\text{O}_3$ -layer essentially consisting of  $\kappa$ - $\text{Al}_2\text{O}_3$  is deposited under conditions disclosed in e.g. EP-A-523 021. The  $\text{Al}_2\text{O}_3$  layer has a thickness of  $0.5-6 \mu\text{m}$ , preferably  $0.5-3 \mu\text{m}$ , and most preferably  $0.5-2 \mu\text{m}$ . Preferably, a further layer ( $<1 \mu\text{m}$ , preferably  $0.1-0.5 \mu\text{m}$  thick) of  $\text{TiN}$  is deposited, but the  $\text{Al}_2\text{O}_3$  layer can be the outermost layer. This outermost layer,  $\text{Al}_2\text{O}_3$  or  $\text{TiN}$ , has a surface roughness  $R_{\text{max}} < 0.4 \mu\text{m}$  over a length of  $10 \mu\text{m}$ . The smooth coating surface can be obtained by a gentle wet-blasting the coating surface with fine grained (400-150 mesh) alumina powder or by brushing (preferably used when  $\text{TiN}$  top coating is present) the edges with brushes based on  $\text{SiC}$  as disclosed in Swedish patent application 9402543-4. The  $\text{TiN}$ -layer, if present, is preferably removed along the cutting edge.

#### Example 1

A. A cemented carbide turning tool insert in style CNMG120408-MM with the composition 10.5 wt-% Co, 1.16 wt-% Ta, 0.28 wt-% Nb and balance WC, with a binder phase highly alloyed with W corresponding to a CW-ratio of 0.87, was coated with an innermost  $0.5 \mu\text{m}$  equiaxed  $\text{TiCN}$ -layer with a high nitrogen content, corresponding to an estimated C/N ratio of 0.05, followed by a  $4.3 \mu\text{m}$



thick layer of columnar TiCN deposited using MT-CVD technique. In subsequent steps during the same coating process a 1.1  $\mu\text{m}$  layer of  $\text{Al}_2\text{O}_3$  consisting of pure  $\kappa$ -phase according to procedure disclosed in EP-A-523 021.

5 A thin, 0.5  $\mu\text{m}$ , TiN layer was deposited, during the same cycle, on top of the  $\text{Al}_2\text{O}_3$ -layer. The coated insert was brushed by a SiC containing nylon straw brush after coating, removing the outer TiN layer on the edge.

B. A cemented carbide turning tool insert in style

10 CNMG120408-MM with the composition of 7.5 wt-% Co, 1.8 wt-% TiC, 3.0 wt-% TaC, 0.4 wt-% NbC, balance WC and a CW-ratio of 0.88. The cemented carbide had a surface zone, about 25  $\mu\text{m}$  thick, depleted from cubic carbides. The insert was coated with an innermost 0.5  $\mu\text{m}$  equiaxed

15 TiCN-layer with a high nitrogen content, corresponding to an estimated C/N ratio of 0.05, followed by a 7.2  $\mu\text{m}$  thick layer of columnar TiCN deposited using MT-CVD technique. In subsequent steps during the same coating process a 1.2  $\mu\text{m}$  layer of  $\text{Al}_2\text{O}_3$  consisting of pure  $\kappa$ -

20 phase according to procedure disclosed in EP-A-523 021. A thin, 0.5  $\mu\text{m}$ , TiN layer was deposited, during the same cycle, on top of the  $\text{Al}_2\text{O}_3$ -layer. The coated insert was brushed by a SiC containing nylon straw brush after coating, removing the outer TiN layer on the edge.

25 C. A competitive cemented carbide turning tool insert in style CNMG120408 from an external leading cemented carbide producer was selected for comparison in a turning test. The carbide had a composition of 9.0 wt-% Co, 0.2 wt-% TiC, 1.7 wt-% TaC, 0.2 wt-% NbC, balance

30 WC and a CW-ratio of 0.90. The insert had a coating consisting of 1.0  $\mu\text{m}$  TiC, 0.8  $\mu\text{m}$  TiN, 1.0  $\mu\text{m}$  TiC and, outermost, 0.8  $\mu\text{m}$  TiN. Examination in light optical microscope revealed no edge treatment subsequent to coating.



D. A competitive cemented carbide turning tool insert in style CNMG120408 from an external leading cemented carbide producer was selected for comparison in a turning test. The cemented carbide had a composition of 5.9 wt-% Co, 3.1 wt-% TiC, 5.6 wt-% TaC, 0.1 wt-% NbC, balance WC and a CW-ratio of 0.95. The cemented carbide had a surface zone, about 30  $\mu\text{m}$  thick, which was enriched in Co content. The insert had a coating consisting of 5.3  $\mu\text{m}$  TiC, 3.6  $\mu\text{m}$  TiCN, outermost, 2.0  $\mu\text{m}$  TiN. Examination in light optical microscope revealed no edge treatment subsequent to coating.

E. A competitive cemented carbide turning tool insert in style CNMG120408 from an external leading cemented carbide producer was selected for comparison in a turning test. The carbide had a composition of 8.9 wt-% Co, balance WC and a CW-ratio of 0.84. The insert had a coating consisting of 1.9  $\mu\text{m}$  TiC, 1.2  $\mu\text{m}$  TiN, 1.5  $\mu\text{m}$   $\text{Al}_2\text{O}_3$  laminated with 3 0.1  $\mu\text{m}$  thick layers of TiN and, outermost, 0.8  $\mu\text{m}$  TiN. Examination in light optical microscope revealed no edge treatment subsequent to coating.

F. A competitive cemented carbide turning tool insert in style CNMG120408 from an external leading cemented carbide producer was selected for comparison in a turning test. The carbide had a composition of 5.4 wt-% Co, 2.7 wt-% TiC, 3.5 wt-% TaC, 2.3 wt-% NbC, balance WC and a CW-ratio of 0.94. The cemented carbide had a surface zone, about 40  $\mu\text{m}$  thick, which was enriched in Co content. The insert had a coating consisting of 5.3  $\mu\text{m}$  TiC, 3.6  $\mu\text{m}$  TiCN, outermost, 2.0  $\mu\text{m}$  TiN. Examination in light optical microscope revealed no edge treatment subsequent to coating.

Inserts from A, B, C, D, E and F were compared in facing of a bar, diameter 180, with two, opposite, flat

sides (thickness 120 mm) in 4LR60 material. Feed 0.25 mm/rev, speed 180 m/min and depth of cut 2.0 mm.

The wear mechanism in this test is chipping of the edge. The inserts with gradient substrates (B, E and F) looked good after three cuts but broke suddenly after about four.

Insert	Number of cuts
A (acc. to invent.)	15
B (outside invention)	5
C (external grade)	9
D (external grade)	9
E (external grade)	4
F (external grade)	4

### Example 2

10 Inserts A, and B from above were selected for a turning test, longitudinal and facing in machineability improved AISI304L stainless steel.

Cutting speed was 250 m/min, feed 0.3 mm/rev and depth of cut 2 mm. Cutting time 1 minute/cycle.

15 The wear mechanism was plastic deformation.

Insert	Number of cycles
B (outside invention)	7
A (acc. to invent.)	4

### Example 3

G. Inserts in geometry TNMG160408-MM with composition and coating according to A above.

20 H. Inserts in geometry TNMG160408-MM with composition and coating according to B above.

I. Inserts in geometry TNMG160408 with composition and coating according to C above.

The inserts G, H and I were tested in longitudinal, dry, turning of a shaft in duplex stainless steel.

Feed 0.3 mm/rev, speed 140 m/min and depth of cut 2 mm. Total cutting time per component was 12 minutes.

Insert G and I got plastic deformation whereas insert H got some notch wear.

5 Two edges of insert G were worn out to produce one component whereas one edge of insert H completed one component and four edges were required to finalise one component using insert I.

Insert	Number of edges/component
H (outside invention)	1
G (acc. to invent.)	2
I (external grade)	4

10

#### Example 4

Inserts A and E from above were selected for a turning test, mainly facing, in a cover rotorcase made in cast AISI316 stainless steel. The cutting was interrupted due to component design.

15

Cutting speed was 180 m/min, feed 0.2 mm/rev and depth of cut 0-2 mm (irregular shape of casting). Cutting time 10.5 minutes/component.

The wear mechanism was a combination of edge chipping and plastic deformation.

20

Insert	Number of components
A (acc. to invent.)	2
E (external grade)	1

#### Example 5

Inserts according to A, B, C and D were selected for a turning test. Internal turning of AISI304 stainless steel valve substrate. Cutting speed was 130 m/min and feed 0.4 mm/rev. The stability was poor due to the boring bar.

25

The wear was chipping of the edge for inserts D and B whereas inserts A and C got plastic deformation.

Insert	Number of components
A (acc. to invent.)	9
D (external grade)	7
C (external grade)	5
B (outside invention)	2

#### Example 6

- 5 Inserts A and C from above were selected for a turning test, roughing of a square bar in AISI316Ti stainless steel. The cutting was interrupted due to component design.

- 10 Cutting speed was 142 m/min, feed 0.2 mm/rev, depth of cut 4 mm. and cutting time 0.13 minutes/component.

The wear was chipping of the edge.

Insert	Number of components
A (acc. to invent.)	25
C (external grade)	15

Claims

1. A cutting tool insert particularly for turning of steel comprising a cemented carbide body and a coating characterised in that said cemented carbide body consists of WC, 6-15, preferably 9-12, wt-% Co and 0.2-1.8 wt-% cubic carbides of Ti, Ta and/or Nb and a highly W-alloyed binder phase with a CW-ratio of 0.78-0.93, preferably 0.80-0.91 and in that said coating comprises
- 10        - a first (innermost) layer of  $TiC_xN_yO_z$  with a thickness of  $<1.5 \mu m$ , and with equiaxed grains with size  $<0.5 \mu m$
- a layer of  $TiC_xN_yO_z$  with a thickness of 2-5  $\mu m$  with columnar grains with an average diameter of  $<5 \mu m$
- 15        - an outer layer of a smooth, fine-grained (0.5-2  $\mu m$ )  $\kappa-Al_2O_3$ -layer with a thickness of 0.5-6  $\mu m$ .
2. Cutting insert according to any of the preceding claims characterised in that the outermost layer is a thin 0.1-1  $\mu m$  TiN-layer.
- 20        3. Cutting insert according to claim 2 characterised in that the outermost TiN-layer has been removed along the cutting edge.
4. Method of making an insert for turning comprising a cemented carbide body and a coating
- 25        characterised in that a WC-Co-based cemented carbide body with a highly W-alloyed binder phase with a CW-ratio of 0.78-0.93 is coated with
- a first (innermost) layer of  $TiC_xN_yO_z$  with  $x+y+z=1$ , preferably  $z<0.5$ , with a thickness of 0.1-1.5  $\mu m$ , with equiaxed grains with size  $<0.5 \mu m$  using known CVD-methods
- 30        - a layer of  $TiC_xN_yO_z$  with  $x+y+z=1$ , preferably with  $z=0$  and  $x>0.3$  and  $y>0.3$ , with a thickness of 2-8  $\mu m$  with columnar grains with a diameter of about  $<5 \mu m$  deposited
- 35        by MTCVD-technique, using acetonitrile as the carbon and

nitrogen source for forming the layer in a preferred temperature range of 850-900 °C.

- a layer of a smooth  $\alpha$ -Al<sub>2</sub>O<sub>3</sub> with a thickness of 0.5-6  $\mu$ m and

5 - preferably a layer of TiN with a thickness of <1  $\mu$ m.

5. Method according to the previous claim characterized in that said cemented carbide body has a cobalt content of 9-12 wt% and 0.4-1.8 wt% cubic  
10 carbides of Ta and Nb.

6. Method according to claim 4 or 5 characterized in that said cemented carbide body has a cobalt content of 10-11 wt%.

7. Method according to claim 4, 5 or 6  
15 characterized in a CW-ratio of 0.82-0.90.

8. Method according to any of the claims 4, 5, 6 and 7 characterized in that the outermost TiN-layer, if present, is removed along the cutting edge.

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 96/01578

## A. CLASSIFICATION OF SUBJECT MATTER

IPC6: C23C 16/30, C23C 16/40, C23C 30/00, B23B 27/14  
According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: C23C, B23B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

JAPIO

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0685572 A2 (MITSUBISHI MATERIALS CORPORATION), 6 December 1995 (06.12.95), page 3, line 21 - page 4, line 39; page 17, claims 1,8,12 --	1-8
Y	EP 0709484 A1 (MITSUBISHI MATERIALS CORPORATION), 1 May 1996 (01.05.96), page 2, line 30 - line 52; page 4; page 6 --	1-8
Y	EP 0686707 A1 (MITSUBISHI MATERIALS CORPORATION), 13 December 1995 (13.12.95), page 2, line 1 - line 18; page 4; line 9 - line 12, claim 1 --	1-8

☒ Further documents are listed in the continuation of Box C.☒ See patent family annex.

\* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

18 February 1997

Date of mailing of the international search report

01-03-1997

Name and mailing address of the ISA/  
Swedish Patent Office  
Box 5055, S-102 42 STOCKHOLM  
Facsimile No. +46 8 666 02 86

Authorized officer

Ingrid Grundfelt  
Telephone No. +46 8 782 25 00



## INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 96/01578

## C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0653499 A1 (SUMITOMO ELECTRIC INDUSTRIES, LTD.), 17 May 1995 (17.05.95), page 13, line 1 - line 41 --	1-8
Y	Patent Abstracts of Japan, Vol 18, No 392, C-1228, abstract of JP, A, 6-108254 (MITSUBISHI MATERIALS CORP), 19 April 1994 (19.04.94), & JP, A, 6-108254 (see p. 3) --	1-8
Y	EP 0408535 A1 (SECO TOOLS AB), 16 January 1991 (16.01.91), column 1, line 5 - line 12; column 5, line 56 - column 6, line 25 --	1-8
Y, P	EP 0693574 A1 (SANDVIK AKTIEBOLAG), 24 January 1996 (24.01.96), claims 5, 6 --	3, 8
Y	US 4643620 A (HIROSHI FUJII ET AL), 17 February 1987 (17.02.87), column 2, line 8 - line 30; column 3, line 42 - line 44; column 3, line 59 - line 66, figure 5C, abstract ----- --	3, 8

**INTERNATIONAL SEARCH REPORT**  
Information on patent family members

03/02/97

International application No.

PCT/SE 96/01578

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A2- 0685572	06/12/95	CN-A- 1121537	01/05/96
		JP-A- 7331443	19/12/95
		JP-A- 7328808	19/12/95
		JP-A- 7328809	19/12/95
		JP-A- 7328810	19/12/95
		JP-A- 8001408	09/01/96
		JP-A- 8001409	09/01/96
		JP-A- 8001410	09/01/96
		JP-A- 8001411	09/01/96
		JP-A- 8090311	09/04/96
EP-A1- 0709484	01/05/96	JP-A- 8118105	14/05/96
		JP-A- 8118108	14/05/96
		JP-A- 8187605	23/07/96
		JP-A- 8187606	23/07/96
EP-A1- 0686707	13/12/95	JP-A- 6190605	12/07/94
EP-A1- 0653499	17/05/95	JP-C- 1441045	30/05/88
		JP-A- 58031118	23/02/83
		JP-B- 62050570	26/10/87
		JP-A- 7100701	18/04/95
		WO-A- 9428191	08/12/94
		JP-A- 7285001	31/10/95
EP-A1- 0408535	16/01/91	SE-T3- 0408535	
		DE-D,T- 69007885	28/07/94
		JP-A- 3138368	12/06/91
		US-A- 5137774	11/08/92
		US-A- 5162147	10/11/92
EP-A1- 0693574	24/01/96	BR-A- 9503375	12/03/96
		CN-A- 1116571	14/02/96
		IL-D- 114674	00/00/00
		JP-A- 8052603	27/02/96
		SE-A- 9402543	21/01/96

**INTERNATIONAL SEARCH REPORT**  
Information on patent family members

03/02/97

International application No.  
PCT/SE 96/01578

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A- 4643620	17/02/87	AU-B- 581847	09/03/89
		AU-A- 2855984	29/11/84
		EP-A,B- 0127416	05/12/84
		SE-T3- 0127416	
		JP-A- 59219122	10/12/84
		US-A- 4755399	05/07/88

---